

LUBBASE[™] 240R

REREFINED GROUP II BASE OIL

PROPERTIES	ASTM METHOD	SPECIFICATION
		Results
Viscosity cSt @ 100°C	D445	7.0
Viscosity cSt @40°C	D445	46.0
Viscosity Index	D2270	108
Copper Corrosion	D130	1a
Aniline Point, °F	D611	234
Pour Point, °C	D97	-12
Specific Gravity, °C	D1298	0.8670
Color	D1500	L1.0
Flash Point, °C	D92	240
Sulfur, ppm	D5185	340
Refractive Index	D1218	1.4771
Sulfated Ash, %	D874	<0.04
Molecular Weight	D2502	470
Noack Distillation, wt%	D5800	8
Volatility, wt%	D972	
Modified Ames Assay	E1687	Pass
Polycyclic Aromatic, %	IP346	<3.0
Clay-Gel, wt%	D2007	
Saturates		89
Aromatics		10.7
Polar Compounds		0.3

Hydrotreated paraffinic process oils, offer great additive solvency, good color stability, low volatility for multifunctional blending. All process oils pass modified Ames test requirements.