

LUBEKO[™] 60T

PROPERTIES	TEST METHOD	SPECIFICATIONS	TYPICAL VALUES
Specific Gravity @25 °C	ASTM D405		0.85138
Viscosity, cSt@ 40 °C	ASTM D445		8.03
Viscosity, cSt @ 100 °C	ASTM D445		2.19
Viscosity, SUS @ 100 °F	ASTM D2161	50.0 – 60.0	54
Viscosity, SUS @ 210 °F	ASTM D2161		33.9
Viscosity Index	ASTM D2270		85
Gravity, API 60° F	ASTM D4052		34.7
Flash Point, COC, °C (°F)	ASTM D0092		163(326)
Pour Point °C (°F)	ASTM D0097		-43(-45)
Color,	ASTM D1500	+28 min	L0.5
Aniline Point, °C (°F)	ASTM D611		84.5(202)