

LUBEKO[™] 80

Test	Method	Results
Appearance	Visual	C&B
Sp Gravity API, @ 60F	D-287	0.8654
Gravity API, @ 60 F	D-5002	32.0
Viscosity @ 40 C cSt	D-445	14.02
Viscosity @ 100 C cSt	D-445	3.128
Viscosity @ 100 F SUS		78.2
Viscosity @ 210 F SUS		36.8
Viscosity Index	D-2270	72.0
COC Flash Point F	D-92	360.
COC Flash Point C	D-92	182.
Pour Point F	D-5950	-27.
Pour Point C	D-5950	-33.
Volatility @ 630F Wt%	D-2887	3.8
Color, Saybolt	D-6304	+30
ASTM color	D-1500	L0.5
Water, Karl Fischer ppm	D-6304	22.
Water Sep., sep. time min	D1401*	5.
Water Sep., emis ml	D1401*	0.
Saturates Wt%	UV Correl.**	100.
Cold Crank at -30C cP	D-5293	1509.